

# DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291  
58 Grey Street  
Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300  
Facsimile: (03) 5367 2991  
Email: [darley@darleyrefractories.com.au](mailto:darley@darleyrefractories.com.au)  
Web: [www.darleyrefractories.com.au](http://www.darleyrefractories.com.au)

**PRODUCT:** **DARLEY STANDARD 26 GROG**

**CLASSIFICATION:** Coarse Grog -5mm + 0.85mm.

**TYPICAL TECHNICAL DATE:**

**CHEMICAL COMPOSITION:**

|                  |     |   |
|------------------|-----|---|
| Silica           | 73  | % |
| Alumina          | 23  |   |
| Ferric Oxide     | 1.5 |   |
| Titania          | 1.1 |   |
| Accessory Oxides | 1.2 |   |

**PHYSICAL PROPERTIES:**

|               |           |                   |
|---------------|-----------|-------------------|
| Bulk Density  | 1030      | kg/m <sup>3</sup> |
| <u>Sizing</u> | <u>mm</u> | <u>Percent</u>    |
| -5.50         | +3.35     | 39 - 41           |
| -3.35         | +1.70     | 31 - 33           |
| -1.70         | +0.85     | 23 - 25           |
| -0.85         | +0.45     | 2 - 4             |

The above data is derived from routine testing of standard brick by independent Laboratories and is not a guaranteed specification. Unless agreed otherwise, supply and testing will be to the appropriate Australian Standard.