DARLEY REFRACTORIES AUSTRALIA PTY. LTD.

A.C.N. 104 582 023 A.B.N. 85 104 582 023



P.O. Box 291 58 Grey Street

Bacchus Marsh Vic. 3340

Telephone: (03) 5367 2300 Facsimile: (03) 5367 2991

Email: <u>darley@darleyrefractories.com.au</u>
Web: <u>www.darleyrefractories.com.au</u>

PRODUCT: HEATSET

CLASSIFICATION: A heat-setting high duty refractory mortar.

INSTALLATION Mortar Required per 1000 RMA 135 Brick REQUIREMENTS:

Trowelled Joints 230 kg
Dipped Joints 130 kg

Water addition for Trowelled Joints
Water addition for Dipped Joints
33 Litres/100 kg
50 Litres/100 kg

PROPERTIES: P.C.E. Orton 27 (1640°C)

SCREEN ANALYSIS: 95% minus 850 micron

<u>CHEMICAL</u>

<u>COMPOSITION:</u>

 $\overline{\text{(Typical)}} \qquad \qquad \text{Si0}_2 \qquad \qquad 72\%$

 Al_2O_3 25

Accessory Oxides 3

Note: The above data is typical for this product

and is not a guaranteed specification and is

subject to reasonable variation.